



UL 94 Flammability Test Report

Manufacturer: Kentek Corporation
5 Jarado Way
Boscawen, NH 03303 USA

Product Name/Number: ACRX-6NDY, ACRX-IR3, ACRX-MW, ACRX-BB2, ACRX-EXC2, ACRX-KTP

Product Description: Laser Protective Windows

Test Report No. TEX-LT-112-18

FLAME RESISTANCE Testing performed in accordance with UL 94 Flammability test against UL 94 Pass/Fail for horizontal flame test.					
Sample #	Time (sec)	Thickness (mm)	Burn Rate RQMTS (mm/min) Max	Burn Rate (mm/min)	Pass/Fail
1	143	2.9	75	31	Pass
2	155	2.9	75	29	Pass
3	166	3.2	40	27	Pass

Equipment Used

Flame Cabinet
Stopwatch
Thickness Gage
Digital Thermometer

Calibration #

8F12-0043-C0
8F12-222200
8F12-095200
8F12-302400

Date: 08/08/2017

Comments: The ACRX- Series Acrylic Laser Protective Sheets are ACCEPTABLE for evaluation to UL 94 HB Flammability test Pass/Fail for FLAME RESISTANCE. (Meets UL 94 HB)

This is for engineering evaluation only and not intended for product acceptance.

Declaration: *This product meets UL 94 HB.*

All information provided in this Certificate of Compliance is accurate, to the best of our knowledge, as of the date this certification was issued.

Bonnie Simmons
Director, Product Development

KENTEK CORPORATION

5 Jarado Way • Boscawen, NH 03303 USA • +1 603-223-4900
info@kenteklaserstore.com • www.kenteklaserstore.com